

*The glossy values reported in the tabel are indicative and referred only to the sample tested by ARPA INDUSTRIALE laboratory according to ISO 2813 e UNI 9149. Glossy values on the same sample can be subject to slightly changing point to point and direction measurement.*

*The glossy is directly influenced by the finish, meanwhile the color basically does not affect it.*

*The chart is periodically updated: verify the last available revision. For the glossy not listed, please, contact the ARPA Customer Service.*

I valori di riflessione speculare elencati in tabella sono indicativi e si riferiscono soltanto al prodotto testato presso il laboratorio di ARPA INDUSTRIALE in accordo con la UNI 9149 e la ISO 2813. I valori di riflessione speculare sullo stesso campione possono variare leggermente da punto a punto e direzione di misura.

La riflessione speculare è direttamente influenzata dalla finitura, mentre il colore non la modifica sostanzialmente.

La tabella viene aggiornata periodicamente: verificare l'ultima revisione disponibile. Per le finiture non elencate si prega di contattare il Customer Service ARPA.

FINISH / FINITURA	Specular gloss / Riflessione speculare		
	at / a 20°	at / a 60°	at / a 85°
Alevè	1	4	20
Cliff	2	15	23
Corallo	2	9	15
Cotton (Metalli)	148	165	95
Farah	1	3	3
Flatting	2	14	15
Ghibli	2	9	7
Larix	1	5	6
Lucida	101	111	100
Luna	1	3	5
Martellata	2	11	22
Mika	1	3	5
Mesh	1	4	4
Mot (Metalli)	3	15	12
Mov (Metalli)	4	24	40
Naked	2	8	7
Opaca	2	16	43
Osl	5	32	66
Pesca	1	3	7
Pixel	1	4	5
Quarzo	1	7	4
R (Erre)	2	14	22
Satinata	11	54	67
Tex	1	6	7
Topface	5	24	20